

**DESCRIPTION**

Stoody 965 deposit is a general purpose hardfacing alloy that offers a good balance of impact and abrasion resistance. It can be used in both metal-to-metal and metal-to-earth applications. Deposits are martensitic and forgeable but not readily machinable. It can be applied to carbon, low alloy, and manganese steels. It is magnetic on carbon and low alloy steels. Analysis and properties are similar to Stoody Self Hardening covered electrode.

**TYPICAL DEPOSIT CHARACTERISTICS**

Abrasion Resistance	Good
Impact Resistance	Good
Hardness on .2 Carbon Steel	HRC 56 – 60
Deposit Layers	2
Magnetic	
On Low Alloy and Carbon Steel	Yes
On Manganese Steel	No
Surface Cross Checks	No

**ALLOY TYPE**

Martensitic Tool Steel

**TYPICAL APPLICATIONS**

- Tillage Tools
- Drag Line Bucket Lips
- Tamper Feet
- Dredge Parts
- Extruder Screws
- Muller Tires

**Stoody Company**

5557 Nashville Road • Bowling Green, KY 42101  
1-800-227-9333

**OPERATIONAL CHARACTERISTICS / WELDING PARAMETERS**

	<b>965-G</b>	
Diameter, In. (mm)	<b>.035 (0.9)</b>	<b>.045 (1.2)</b>
Current, Amp. DCRP	80 – 130	150 – 200
Voltage	15 – 20	25 – 29
Wire Extension	1/2" – 5/8"	1/2" – 3/4"
Shielding Gas	75/25, CO <sub>2</sub> , or 98/2	98/2 or 75/25
Position	All	Flat or Horizontal

	<b>965-G</b>	<b>965-O</b>
Diameter, In. (mm)	<b>1/16 (1.6)</b>	<b>1/16 (1.6)</b>
Current, Amp. DCRP	200 – 250	200 – 250
Voltage	27 – 31	27 – 31
Wire Extension	3/4" – 1"	3/4" – 1 1/4"
Shielding Gas	98/2 or 75/25	None or CO <sub>2</sub>
Position	Flat or Horizontal	Flat or Horizontal

**STANDARD SIZES & PACKAGING**

<b>965-G</b>		
<b>Diameter</b>	<b>Packaging</b>	<b>Part #</b>
.035" (0.9mm)	5# PS-LLW	11929300
.045" (1.2mm)	10# PS	11142300
.045" (1.2mm)	33# WB	11423100
1/16" (1.6mm)	33# WB	11501500
1/16" (1.6mm)	50# PP	11823900
1/16" (1.6mm)	200# HP	11864500
1/16" (1.6mm)	400# NTP Drum	11875500

<b>965-O</b>		
<b>Diameter</b>	<b>Packaging</b>	<b>Part #</b>
1/16" (1.6mm)	10# PS	11427200
1/16" (1.6mm)	33# WB	11427100
1/16" (1.6mm)	50# PP	11427000

PDS-CRC-W-001

Revision 1  
08/06/02

Notice: The information contained or otherwise referenced herein is presented only as "typical", without guarantee or warranty. Stoody expressly disclaims any liability from any reliance thereon. Typical data are those obtained when welded and tested in accordance with Stoody's internal procedures. Other tests and procedures may produce different results. No data is to be construed as a recommendation for any welding condition or technique not controlled by Stoody.